

## Product information | TECHNICAL DATA SHEET

### MAGNETIC CHALK BOARD PAINT

400 ml, 9,7 Oz, 275 g.

#### GENERAL DESCRIPTION

Water-based, magnetic paint. High opacity, matt finish and ideal for interior decorations, walls and columns to obtain magnetic finishes.

#### FEATURES

- Fast drying.
- Magnético
- Easy to clean with a damp cloth.
- Does not contain lead.
- Good adhesion.
- Easy to apply and repainting.
- Compatible with chalk and Montana Chalk Markers.

#### APPLICATIONS

Due to the nature of this product, we recommend an adequate preparation of the surface prior to painting. Surfaces must be clean, dry and smooth. We recommend using an adequate primer for porous surfaces. This products may be used on a multitude of surfaces: plasterboard, solid wood, plywood, brick, metal surfaces, etc. Due to its low odor this product is suitable for painting indoors.

- Fine arts
- DIY
- Crafts
- Domestic

#### INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. When painting porous materials, apply sufficient primer first.
- We recommend applying 5-7 coats to obtain a strong magnetic effect, but this may be varied depending on the type of magnet used. Wait 15 minutes before applying the next coat. If you need a stronger magnetic effect, apply more coats. It is always better to apply multiple thin coats that one thick coat. Turn the aerosol upside down to purge after use. If the cap gets blocked, replace it with a new one.
- Reverse the aerosol valve to purge after use, if the actuator gets blocked, replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Chalkboards may be cleaned after use with a damp cloth. With other types of products for similar use such as markers, damp cloths may leave some leftover residual.
- Request safety datasheets.

#### PHYSICAL PROPERTIES

Color:	Black
Brightness 60° (ASTM D-523 ISO 2813)	<10%
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Total drying (ASTM D-1640 ISO 1517):	20'
Thickness of dry layer (ASTM D-823 ISO 2808):	20 µ/capa (2 coats)
Theoretical yield ( continuous painting):	0,2 m² (6 coats)
Product life:	>5 years
Recoating:	After 10'
Heat resistance of paint:	160°C
Condition for application:	T° environment min 8°C
	T° surface min de 5°C-50°C
	Humidity max 85% R.H.P

\*Date last reviewed: 25/10/2017

#### APPEARANCE



#### LABEL



#### CAP SYSTEM



#### PACKAGING

Nominal capacity 400 ml.  
Heat resistance of packaging: <50°C  
Propellant: BP

Box (6 units)  
205 X 140 X 200 mm.



#### CAUTION

